

ARMOUR

METALLIC INTERLOCKED POLYMER FLOOR FINISH



DESCRIPTION

This floor finish is for those who want the **highest gloss and wear** with the **least amount of labor**. This 25% solids, metal cross linked, polymer finish gives your floors a depth of gloss like you've never seen before. **One coat does the job of two coats** of an ordinary finish. This durable finish is **detergent-resistant and non scuffing** which makes it a real labor-saver. It is suitable for use on all floors and may be maintained by damp mopping. This product performs exceptionally well with either spray buffing or high speed buffing, and its **excellent leveling** makes it easy to apply.

BENEFITS - FEATURES

- * Durability
- * Self-leveling
- * Appearance
- * Versatile

ADVANTAGES

- * Extended wear and superior protection
- * High-gloss, black mark, and detergent resistant
- * Easy application with little or no mop drag
- * May be used with or without floor sealer

WHERE TO USE

- * Resilient Flooring
- * Sealed Wood Flooring
- * Terrazzo
- * Linoleum

RECOMMENDED FOR

- * Schools
- * Institutions
- * Hospitals
- * Nursing Homes
- * Restaurants
- * Cafeterias
- * Shopping Malls
- * Show Rooms
- * Office Buildings
- * Government Buildings
- * Hotels
- * Motels
- * Churches
- * Airports
- * Athletic/Country Clubs
- * Public Buildings

DIRECTIONS

1. Strip all old wax or finish. Rinse if necessary and allow to dry.
2. Apply a uniform coat of finish with a clean mop or applicator.
3. Allow to dry for 20-30 minutes before applying subsequent coats.
4. Apply a sufficient number of coats to provide adequate protection for the floor.

No maintenance program will work efficiently without an effective level of protection.

Requires no authorization by USDA prior to its use in offices and other similar non processing areas.

SPECIFICATIONS

Fragrance.....Mild	Recoat.....Very good	Coverage.....3,000-4,000 sq. ft./gal.
Gloss.....1 coat 80-85 2 coats 97-98	Heel mark resistance.....Very good	Slip resistance (James machine).....0.61-0.65
pH.....8.7	Shelf life.....2 yr. min.	Total solids.....29.6%
Density.....8.4 lbs./gal.	Freeze/thaw stability.....3 cycles	Nonvolatile solids.....25%
Leveling.....Excellent	Powdering resistance.....Excellent	
	Drying time.....20-30 min.	

Another Exclusive Product of

ULTRA-CHEM INC.

Kansas City - Phoenix 800-451-0726

